

DESCRIPTION

- Two-part, alkoxy-cure, electrically conductive RTV silicone colored green-gray
- Designed for enhanced performance in extreme low and high temperatures
- Maintains electric conductivity over a broad service temperature range
- 100:0.5 Mix Ratio (Base: Catalyst)

APPLICATION

- For applications requiring low volatility
- Well suited for form-in-place conductive gaskets
- Use as a thermally or electrically conductive interface material
- For applications requiring low temperature cure

PROPERTIES

TYPICAL PROPERTIES	AVERAGE RESULT	ASTM	NT-TM
Uncured:			
Appearance*	Green-gray	D2090	002
Flow, Base* (0.375" plunge for 30 seconds, mix vigorously for 5 minutes prior to testing)	4 inches (10.2 cm)	D2202	019
Work Time*	2.5 hours	-	008
Cured: 7 days minimum @ ambient temperature and humidity			
Specific Gravity*	3.23	D792	003
Durometer, Type A*	75	D2240	006
Tensile Strength*	300 psi (2.1 MPa)	D412	007
Elongation*	70%	D412	007
Tear Strength*	55 ppi (9.7 kN/m)	D624	009
Lap Shear Strength* (primed w/ SP-120)	185 psi (1.3 MPa)	D1002	010
Volume Resistivity* (@ 200+/-5°C)	0.003 ohm-cm	D257, D4496	040



TYPICAL PROPERTIES	AVERAGE RESULT	ASTM	NT-TM
Thermal Conductivity	1.5 W/mK (36 x 10 ⁻⁴ cal/(cm·sec·°C))	C1045, C177	101

*Properties tested on a lot-to-lot basis. Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

INSTRUCTIONS FOR USE

Mixing

Thoroughly stir base prior to weighing for curing agent addition, as the product separates. Mix 100 parts base to 0.5 part catalyst by weight, just prior to use.

Vacuum Deaeration

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all safety precautions. Slowly apply full vacuum to a container rated for use and at least four times the volume of material being deaerated. Hold vacuum until bulk deaeration is complete.

Note: Some bonding applications may require the use of a primer. NuSil Technology's SP-120 is recommended.

Adjustable Cure Schedule

Product cures at a wide range of cure times and temperatures to accommodate different production needs. Contact NuSil Technology for details.

Packaging

50 Gram Kit
100 Gram Kit
500 Gram Kit

Warranty

6 Months

OPERATING TEMPERATURE

The operating temperature range of a silicone in any application is dependent on many variables, including but not limited to: temperature, time of exposure, type of atmosphere, exposure of the material's surface to the atmosphere, and mechanical stress. In addition, a material's physical properties will vary at both the high and low end of the operating temperature range. This type of silicone typically remains flexible at extremely low temperatures and has been known to perform at -140°C (-220°F) as well as resist breakdown at elevated temperatures up to 300°C (572°F). The user is responsible to verify performance of a material in a specific application.

RoHS AND REACH COMPLIANCE

EPM-2463 is compliant with the Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment (RoHS) regulation contained in Article 4(1) of the European Parliament and Council's Directive 2002/95/EC. RoHS mandates that manufacturers



restrict the use of lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls, polychlorinated biphenyls, and polybrominated diphenyl ethers in electrical and electronic equipment.

EPM-2463 is also compliant with the Registration, Evaluation, and Authorization of Chemicals (REACH) regulation (European Union 1907/2006). EPM-2463 does not contain any of the 16 chemicals identified as Substances of Very High Concern (SVHC) by the European Chemicals Agency (ECHA), which oversees REACH compliance.

Please contact NuSil Technology's Regulatory Compliance department with any questions or for further assistance.

SPECIFICATIONS

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 6 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies.



Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.



Polymer Systems *PST* Technology Limited



Silicone Sales & Services
UK - Ireland - Benelux

© 2014 - Polymer Systems Technology Limited™
Unit 2. Network 4. Cressex Business Park,
Lincoln Road, High Wycombe, Bucks. HP12 3RF

Phone +44 (0) 1494 446610
Web: <http://www.silicone-polymers.co.uk>
Email: sales@silicone-polymers.co.uk

